

In the Claims

1. (Currently Amended) A multilayer film comprising:
a substrate film (a),
a hard coat layer (b) containing a (meth)acrylate compound,
an electrically conductive layer (c) having a thickness of 0.06 to 0.12 μm and containing 70% to 90% by weight of electrically conductive particles, and
a resin layer (d) having a thickness of 0.01 to 1.0 μm and containing a fluorine-containing copolymer having a vinyl ether in principal chain and silica particles with a particle size of 0.001 μm to 0.2 μm in two or more particle size distributions,
the layers being disposed on at least one face of the substrate film (a), wherein the resin layer (d) has fine irregularities on the surface and an arithmetic average surface roughness R_a ranging from 0.004 μm to 0.020 μm and the surface of the resin layer (d) of the multilayer film has a reflectance of less than 2%.
2. (Original) The multilayer film according to claim 1, wherein the haze of the multilayer film is less than 3%.
3. (Original) The multilayer film according to claim 1, wherein the substrate film (a) contains a polymer containing one selected from the group consisting of an ester, an olefin, an acetate, styrene, a carbonate, a sulfone, ether ethyl ketone, an imide, fluorine, a nylon, an acrylate, and an aliphatic olefin.
4. (Original) The multilayer film according to claim 3, wherein the substrate film (a) contains a polymer containing one selected from the group consisting of the ester, the acetate, and the acrylate.

5. (Cancelled)
6. (Original) The multilayer film according to claim 1, wherein the electrically conductive particles of the electrically conductive layer (c) contain a metal oxide.
- 7-10. (Cancelled)
11. (Original) The multilayer film according to claim 1, wherein the resin layer (d) contains a silane coupling agent represented by the formula $R(1)_aR(2)_bSiX_{4-(a+b)}$, or a hydrolysate of the agent, or a product obtained by subjecting the hydrolysate to reaction, wherein R(1) and R(2) independently represent a hydrocarbon group having an alkyl group, an alkenyl group, an allyl group, a halogen group, an epoxy group, an amino group, a mercapto group, a methacryloxy group, or a cyano group, X represents a hydrolyzable substituent selected from the group consisting of an alkoxyl group, an alkoxyalkoxy group, a halogen group, and an acyloxy group, a and b are independently equal to zero, one, or two, and the sum of a and b is equal to one, two, or three.
12. (Original) The multilayer film according to claim 1, wherein the fluorine compound contained in the resin layer (d) has an alkoxysilyl group.
13. (Original) A display film including the multilayer film according to claim 1.
14. (Original) A display including the multilayer film according to claim 13.
15. (Original) A display filter including the multilayer film according to claim 1.
16. (Original) A front protector panel, including the display filter according to claim 15, for plasma display panels.
17. (Original) A plasma display including the front protector panel for plasma display panels according to claim 16.

18. (Previously Presented) The multilayer film according to Claim 1, further comprising a cross-linkable compound in the resin layer (d).
19. (Previously Presented) The multilayer film according to Claim 1, wherein the fluorine-containing copolymer contains a fluorine-containing olefin chain with a fluorine content of 30% or more.
20. (Previously Presented) The multilayer film according to Claim 19, wherein the fluorine-containing copolymer contains 20% to 70% of a repeating unit derived from the fluorine-containing olefin compound.
21. (Previously Presented) The multilayer film according to Claim 1, wherein the fluorine-containing copolymer contains 10% to 70% of a repeating unit derived from the vinyl ether-containing compound.